

Quality Certificate of cement

Type of cement : **CEM II/A-V 42,5R**

Requirements acc. to: EN 197-1:2011

Values obtained for the period of: **August 2022**

	Unit	Results	Requirements acc. to: EN 197-1:2011
--	------	---------	--

1.Properties (by standards)

Compressive strength			
Early strength, after 2 days	MPa	26,0	≥ 20
Standard strength, after 28 days (results from previous month)	MPa	55,0	≥ 42,5 i ≤ 62,5
Initial setting time	min	180	≥ 60
Expansion of cement	mm	1,0	≤ 10
Sulfate content (as SO ₃)	%	2,83	≤ 4,0
Chloride content Cl ⁻	%	0,072	≤ 0,10
Loss on ignition ^{a)}	%	-	-
Insoluble residues ^{a)}	%	-	-

2. Additional information

Laser particle size distribution passing 8 µm/32 µm	%	31/73	-
--	---	-------	---

a)only for CEM I and CEM III

Anna Kozłowska

Kierownik Jakości
[Signature]
Cementownia Kujawy w Bielawach

.....
stamp/signature