

## Quality Certificate of cement

Type of cement : **CEM II/A-V 42,5R**

Requirements acc. to: EN 197-1:2011

Values obtained for the period of: **June 2023**

|  | Unit | Results | Requirements acc. to:<br>EN 197-1:2011 |
|--|------|---------|----------------------------------------|
|--|------|---------|----------------------------------------|

### 1. Properties (by standards)

|                                                                                  |     |       |                           |
|----------------------------------------------------------------------------------|-----|-------|---------------------------|
| Compressive strength                                                             |     |       |                           |
| Early strength, after 2 days                                                     | MPa | 26,4  | $\geq 20$                 |
| Standard strength, after 28 days<br><small>(results from previous month)</small> | MPa | 56,1  | $\geq 42,5$ i $\leq 62,5$ |
| Initial setting time                                                             | min | 205   | $\geq 60$                 |
| Expansion of cement                                                              | mm  | 1,0   | $\leq 10$                 |
| Sulfate content (as SO <sub>3</sub> )                                            | %   | 2,75  | $\leq 4,0$                |
| Chloride content Cl <sup>-</sup>                                                 | %   | 0,065 | $\leq 0,10$               |
| Loss on ignition <sup>a)</sup>                                                   | %   | -     | -                         |
| Insoluble residues <sup>a)</sup>                                                 | %   | -     | -                         |

### 2. Additional information

|                                                        |   |       |   |
|--------------------------------------------------------|---|-------|---|
| Laser particle size distribution<br>passing 8 µm/32 µm | % | 32/74 | - |
|--------------------------------------------------------|---|-------|---|

a) only for CEM I and CEM III

*Anna Kozłowska*

Kierownik Jakości  
*Kozłowska*  
Cementownia Kujawy w Bielawach

.....  
stamp/signature