

**KUJAWY CEMENT
PLANT IN BIELAWY****Holcim Polska S.A.**
Kujawy Cement Plant
Technical Supporttel.: (52) 58 65 000, fax: (52) 58 65 011
tel.: (41) 24 87 533, fax: (41) 24 87 531

Quality Certificate of cement

Type of cement : **CEM I 42,5R**Requirements acc. to: **EN 197-1:2011**Values obtained for the period of: **February 2024**

	Unit	Results	Requirements acc. to: EN 197-1:2011
--	------	---------	--

1. Properties (by standards)

Compressive strength			
Early strength, after 2 days	MPa	24,7	≥ 20
Standard strength, after 28 days <small>(results from previous month)</small>	MPa	58,2	≥ 42,5 i ≤ 62,5
Initial setting time	min	200	≥ 60
Expansion of cement	mm	1,0	≤ 10
Sulfate content (as SO ₃)	%	2,99	≤ 4,0
Chloride content Cl ⁻	%	0,049	≤ 0,10
Loss on ignition ^{a)}	%	3,54	≤ 5,0
Insoluble residues ^{a)}	%	0,82	≤ 5,0

2. Additional information

Laser particle size distribution passing 8 μm/32 μm	%	31/74	-
--	---	-------	---

a) only for CEM I and CEM III

Anna Kozłowska
Kierownik Jakości
stampa i podpis
Cementownia Kujawy w Bielawach

Holcim Polska S.A.ul. Warszawska 110, 28-366 Małogoszcz
NIP: 526-10-60-765, REGON: 011843520
KRS: 0000062569 (Sąd Rejonowy w Kielcach X Wydział Gospodarczy KRS)
Kapitał akcyjny: 811.329.500 opłacony w pełni, nr rejestracyjny BDO 000001937

www.holcim.pl